

# LAL BABA SEAMLESS TUBES PVT.LTD.

Haldia, West Bengal - 721657

Technical Delivery Condition



Sl. No.	Section	Description as per Specification																																																																																				
1	<b>Specification</b>	ASTM A53 B/A106 Gr.B / A333 Gr. 1 & 6 / CSAZ245 Gr. 290 CAT- I / API 5L Gr.B / X42 PSL-1/OD 60.30 X WT 3.90 MM / MADE IN INDIA																																																																																				
2	<b>Size</b>	OD 60.30 X WT 3.90 MM																																																																																				
3	<b>Application</b>	ASTM A53 B - Standard Specification for seamless Pipe A106 Gr.B - Standard Specification for Seamless Carbon Steel Pipe for High-Temperature Service A333 Gr. 1 & 6 - Standard Specification for Seamless Pipe for Low-Temperature Service CSAZ245 Gr. 290 CAT- I - Petroleum and Natural Gas Industry Pipeline Systems and Materials API 5L Gr.B / X42 PSL-1 - Products for the Petroleum and Natural Gas Industry																																																																																				
4	<b>Process of Manufacture</b>	Cold drawn seamless																																																																																				
5	<b>Specification Grade</b>	<table border="1"> <thead> <tr> <th></th> <th>ASTM A53 B</th> <th>A106 Gr.B</th> <th>A333 Gr. 1&amp;6</th> <th>CSAZ245 Gr. 290 CAT- I</th> <th>API 5L Gr.B / X42 PSL-1</th> <th>Lalbaba Offer</th> </tr> </thead> <tbody> <tr> <td><b>Yst in Mpa</b></td> <td>240 Min</td> <td>205 Min</td> <td>240 min</td> <td>290-495</td> <td>290 Min</td> <td>320 - 350</td> </tr> <tr> <td><b>UTS in Mpa</b></td> <td>415 Min</td> <td>380 Min</td> <td>415 min</td> <td>414-760</td> <td>415 Min</td> <td>440 - 470</td> </tr> <tr> <td><b>E%</b></td> <td>30% Min</td> <td>35% Min</td> <td>30 min</td> <td>22 min</td> <td>As per given formula in spec</td> <td>38 - 47</td> </tr> <tr> <td><b>Hardness</b></td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>70 - 80</td> </tr> <tr> <td><b>Bend test</b></td> <td>OD ≤ 60.30 mm</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Applicable</td> <td>OD ≤ 60.30 mm</td> <td>OK</td> </tr> <tr> <td><b>Flattening</b></td> <td>OD ≥ 60.30mm</td> <td>Applicable</td> <td>Applicable</td> <td>Applicable</td> <td>OD ≥ 60.30mm</td> <td>OK</td> </tr> <tr> <td><b>Flaring</b></td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>Not Applicable</td> <td>OK</td> </tr> <tr> <td><b>Impact</b></td> <td>Not Applicable</td> <td>Applicable as per Spec</td> <td>Applicable as per Spec</td> <td>Applicable as per Spec</td> <td>Not Applicable</td> <td>OK</td> </tr> </tbody> </table>		ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer	<b>Yst in Mpa</b>	240 Min	205 Min	240 min	290-495	290 Min	320 - 350	<b>UTS in Mpa</b>	415 Min	380 Min	415 min	414-760	415 Min	440 - 470	<b>E%</b>	30% Min	35% Min	30 min	22 min	As per given formula in spec	38 - 47	<b>Hardness</b>	Not Applicable	Not Applicable	Not Applicable	Not Applicable	Not Applicable	70 - 80	<b>Bend test</b>	OD ≤ 60.30 mm	Not Applicable	Not Applicable	Applicable	OD ≤ 60.30 mm	OK	<b>Flattening</b>	OD ≥ 60.30mm	Applicable	Applicable	Applicable	OD ≥ 60.30mm	OK	<b>Flaring</b>	Not Applicable	Not Applicable	Not Applicable	Not Applicable	Not Applicable	OK	<b>Impact</b>	Not Applicable	Applicable as per Spec	Applicable as per Spec	Applicable as per Spec	Not Applicable	OK																					
	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer																																																																																
<b>Yst in Mpa</b>	240 Min	205 Min	240 min	290-495	290 Min	320 - 350																																																																																
<b>UTS in Mpa</b>	415 Min	380 Min	415 min	414-760	415 Min	440 - 470																																																																																
<b>E%</b>	30% Min	35% Min	30 min	22 min	As per given formula in spec	38 - 47																																																																																
<b>Hardness</b>	Not Applicable	Not Applicable	Not Applicable	Not Applicable	Not Applicable	70 - 80																																																																																
<b>Bend test</b>	OD ≤ 60.30 mm	Not Applicable	Not Applicable	Applicable	OD ≤ 60.30 mm	OK																																																																																
<b>Flattening</b>	OD ≥ 60.30mm	Applicable	Applicable	Applicable	OD ≥ 60.30mm	OK																																																																																
<b>Flaring</b>	Not Applicable	Not Applicable	Not Applicable	Not Applicable	Not Applicable	OK																																																																																
<b>Impact</b>	Not Applicable	Applicable as per Spec	Applicable as per Spec	Applicable as per Spec	Not Applicable	OK																																																																																
7	<b>Chemical composition</b>	<table border="1"> <thead> <tr> <th></th> <th>ASTM A53 B</th> <th>A106 Gr.B</th> <th>A333 Gr. 1&amp;6</th> <th>CSAZ245 Gr. 290 CAT- I</th> <th>API 5L Gr.B / X42 PSL-1</th> <th>Lalbaba Offer</th> </tr> </thead> <tbody> <tr> <td><b>%C</b></td> <td>0.30 Max</td> <td>0.30 Max</td> <td>0.30 Max</td> <td>0.26 Max</td> <td>0.28 Max</td> <td>0.17 - 0.22</td> </tr> <tr> <td><b>%Mn</b></td> <td>0.29-1.06</td> <td>-</td> <td>0.40-1.06</td> <td>2.00 Max</td> <td>1.30 Max</td> <td>1.10 - 1.25</td> </tr> <tr> <td><b>%Si</b></td> <td>0.10 Min</td> <td>-</td> <td>-</td> <td>0.50 Max</td> <td>-</td> <td>0.10 - 0.35</td> </tr> <tr> <td><b>%P</b></td> <td>0.035 Max</td> <td>0.025</td> <td>0.025</td> <td>0.030 Max</td> <td>0.030 Max</td> <td>0.025 Max</td> </tr> <tr> <td><b>%S</b></td> <td>0.035 Min</td> <td>0.025</td> <td>0.025</td> <td>0.035 Max</td> <td>0.030 Max</td> <td>0.025 Max</td> </tr> <tr> <td><b>%Cr</b></td> <td>0.40 Max</td> <td>-</td> <td>-</td> <td>-</td> <td>-</td> <td>0.40 Max</td> </tr> <tr> <td><b>%Cu</b></td> <td>0.40 Max</td> <td>-</td> <td>-</td> <td>-</td> <td>-</td> <td>0.40 Max</td> </tr> <tr> <td><b>%Mo</b></td> <td>0.15 Max</td> <td>-</td> <td>-</td> <td>-</td> <td>-</td> <td>0.15 Max</td> </tr> <tr> <td><b>%Ni</b></td> <td>0.40 Max</td> <td>-</td> <td>-</td> <td>-</td> <td>-</td> <td>0.40 Max</td> </tr> <tr> <td><b>%V</b></td> <td>0.08 Max</td> <td>-</td> <td>-</td> <td>0.11 Max</td> <td>-</td> <td>0.08 Max</td> </tr> <tr> <td><b>Others</b></td> <td>-</td> <td>-</td> <td>-</td> <td>-</td> <td>Nb + V + Ti ≤ 0.15</td> <td>Nb + V + Ti ≤ 0.15</td> </tr> </tbody> </table>		ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer	<b>%C</b>	0.30 Max	0.30 Max	0.30 Max	0.26 Max	0.28 Max	0.17 - 0.22	<b>%Mn</b>	0.29-1.06	-	0.40-1.06	2.00 Max	1.30 Max	1.10 - 1.25	<b>%Si</b>	0.10 Min	-	-	0.50 Max	-	0.10 - 0.35	<b>%P</b>	0.035 Max	0.025	0.025	0.030 Max	0.030 Max	0.025 Max	<b>%S</b>	0.035 Min	0.025	0.025	0.035 Max	0.030 Max	0.025 Max	<b>%Cr</b>	0.40 Max	-	-	-	-	0.40 Max	<b>%Cu</b>	0.40 Max	-	-	-	-	0.40 Max	<b>%Mo</b>	0.15 Max	-	-	-	-	0.15 Max	<b>%Ni</b>	0.40 Max	-	-	-	-	0.40 Max	<b>%V</b>	0.08 Max	-	-	0.11 Max	-	0.08 Max	<b>Others</b>	-	-	-	-	Nb + V + Ti ≤ 0.15	Nb + V + Ti ≤ 0.15
	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer																																																																																
<b>%C</b>	0.30 Max	0.30 Max	0.30 Max	0.26 Max	0.28 Max	0.17 - 0.22																																																																																
<b>%Mn</b>	0.29-1.06	-	0.40-1.06	2.00 Max	1.30 Max	1.10 - 1.25																																																																																
<b>%Si</b>	0.10 Min	-	-	0.50 Max	-	0.10 - 0.35																																																																																
<b>%P</b>	0.035 Max	0.025	0.025	0.030 Max	0.030 Max	0.025 Max																																																																																
<b>%S</b>	0.035 Min	0.025	0.025	0.035 Max	0.030 Max	0.025 Max																																																																																
<b>%Cr</b>	0.40 Max	-	-	-	-	0.40 Max																																																																																
<b>%Cu</b>	0.40 Max	-	-	-	-	0.40 Max																																																																																
<b>%Mo</b>	0.15 Max	-	-	-	-	0.15 Max																																																																																
<b>%Ni</b>	0.40 Max	-	-	-	-	0.40 Max																																																																																
<b>%V</b>	0.08 Max	-	-	0.11 Max	-	0.08 Max																																																																																
<b>Others</b>	-	-	-	-	Nb + V + Ti ≤ 0.15	Nb + V + Ti ≤ 0.15																																																																																
8	<b>NDT</b>	<table border="1"> <thead> <tr> <th>Test</th> <th>Specification</th> <th>Lalbaba Offer</th> </tr> </thead> <tbody> <tr> <td><b>ECT</b></td> <td>Applicable as per specification ASME E390</td> <td>As per specification ASME E390 with minimum 0.8 mm drill hole</td> </tr> <tr> <td><b>UT</b></td> <td>Applicable as per specification ASME E213</td> <td>As per specification ASME E213 with minimum 0.3 mm notch depth</td> </tr> </tbody> </table>	Test	Specification	Lalbaba Offer	<b>ECT</b>	Applicable as per specification ASME E390	As per specification ASME E390 with minimum 0.8 mm drill hole	<b>UT</b>	Applicable as per specification ASME E213	As per specification ASME E213 with minimum 0.3 mm notch depth																																																																											
Test	Specification	Lalbaba Offer																																																																																				
<b>ECT</b>	Applicable as per specification ASME E390	As per specification ASME E390 with minimum 0.8 mm drill hole																																																																																				
<b>UT</b>	Applicable as per specification ASME E213	As per specification ASME E213 with minimum 0.3 mm notch depth																																																																																				
9	<b>Hydrostatic Test</b>	<table border="1"> <thead> <tr> <th>Pressure</th> <th>ASTM A53 B</th> <th>A106 Gr.B</th> <th>A333 Gr. 1&amp;6</th> <th>CSAZ245 Gr. 290 CAT- I</th> <th>API 5L Gr.B / X42 PSL-1</th> <th>Lalbaba Offer</th> </tr> </thead> <tbody> <tr> <td>2500 PSI pressure minimum 5Sec holding time</td> <td>2500 PSI pressure minimum 5Sec holding time</td> <td>1000 PSI pressure minimum 5Sec holding time</td> <td>1000 PSI pressure minimum 5Sec holding time</td> <td>20.7 Mpa pressure minimum 5Sec holding time</td> <td>2500 PSI pressure minimum 5Sec holding time</td> <td>2500 PSI 5 Sec holding time</td> </tr> </tbody> </table>	Pressure	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer	2500 PSI pressure minimum 5Sec holding time	2500 PSI pressure minimum 5Sec holding time	1000 PSI pressure minimum 5Sec holding time	1000 PSI pressure minimum 5Sec holding time	20.7 Mpa pressure minimum 5Sec holding time	2500 PSI pressure minimum 5Sec holding time	2500 PSI 5 Sec holding time																																																																						
Pressure	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer																																																																																
2500 PSI pressure minimum 5Sec holding time	2500 PSI pressure minimum 5Sec holding time	1000 PSI pressure minimum 5Sec holding time	1000 PSI pressure minimum 5Sec holding time	20.7 Mpa pressure minimum 5Sec holding time	2500 PSI pressure minimum 5Sec holding time	2500 PSI 5 Sec holding time																																																																																
10	<b>Dimension Tolerance (mm)</b>	<table border="1"> <thead> <tr> <th>Parameter</th> <th>ASTM A53 B</th> <th>A106 Gr.B</th> <th>A333 Gr. 1&amp;6</th> <th>CSAZ245 Gr. 290 CAT- I</th> <th>API 5L Gr.B / X42 PSL-1</th> <th>Lalbaba Offer</th> </tr> </thead> <tbody> <tr> <td><b>OD</b></td> <td>10.30 to 48.30 ±0.40 Over OD 48.30 to 114.30 ±0.80</td> <td>10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8</td> <td>10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8</td> <td>OD ±1.00%</td> <td>&lt; 60.3 : -0.80/+0.40 ≥ 60.30 to 168.30 : ±0.0075D</td> <td>OD +/-0.20 MM</td> </tr> <tr> <td><b>WT/ID</b></td> <td>OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%</td> <td>OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%</td> <td>OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%</td> <td>WT +18.0%, -12.5%</td> <td>≤4.0 : -0.50/+0.60 &gt; 4.0 : +0.150T-0.125T</td> <td>WT +/-0.30 MM</td> </tr> </tbody> </table>	Parameter	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer	<b>OD</b>	10.30 to 48.30 ±0.40 Over OD 48.30 to 114.30 ±0.80	10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8	10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8	OD ±1.00%	< 60.3 : -0.80/+0.40 ≥ 60.30 to 168.30 : ±0.0075D	OD +/-0.20 MM	<b>WT/ID</b>	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	WT +18.0%, -12.5%	≤4.0 : -0.50/+0.60 > 4.0 : +0.150T-0.125T	WT +/-0.30 MM																																																															
Parameter	ASTM A53 B	A106 Gr.B	A333 Gr. 1&6	CSAZ245 Gr. 290 CAT- I	API 5L Gr.B / X42 PSL-1	Lalbaba Offer																																																																																
<b>OD</b>	10.30 to 48.30 ±0.40 Over OD 48.30 to 114.30 ±0.80	10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8	10.30 to 48.30-0.40/+0.80 Over OD 48.30 to 114.30 ±0.8	OD ±1.00%	< 60.3 : -0.80/+0.40 ≥ 60.30 to 168.30 : ±0.0075D	OD +/-0.20 MM																																																																																
<b>WT/ID</b>	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	OD 10.30 to 73 +20%,-12.5%. OD 88.90 to 450 +22.5%,-12.5%	WT +18.0%, -12.5%	≤4.0 : -0.50/+0.60 > 4.0 : +0.150T-0.125T	WT +/-0.30 MM																																																																																
11	<b>Heat Treatments Condition</b>	Heat treated Above 650°C																																																																																				
12	<b>Surface condition</b>	-																																																																																				
13	<b>End Condition</b>	Plain end / Bevel end																																																																																				
14	<b>Straightness</b>	Reasonably staright																																																																																				
15	<b>Ovality</b>	-																																																																																				
16	<b>Eccentricity</b>	-																																																																																				
17	<b>Stencil Marking</b>	ASTM A53 B/A106 Gr.B / A333 Gr. 1 & 6 / CSAZ245 Gr. 290 CAT- I / API 5L Gr.B / X42 PSL-1/OD 60.30 X WT 3.90 MM / MADE IN INDIA																																																																																				
18	<b>Coating</b>	Bare/Rust preventive coating																																																																																				

Reach Us At

Sales Office 1 - Delhi, India

Sales@lalbabagroup.com

Sales Office 2 - Pune, Maharashtra

export@lalbabagroup.com

